



US006860980B2

(12) **United States Patent**
Locascio et al.

(10) **Patent No.:** **US 6,860,980 B2**
(45) **Date of Patent:** **Mar. 1, 2005**

(54) **POLYELECTROLYTE DERIVATIZATION OF MICROFLUIDIC DEVICES**

(75) Inventors: **Laurie E. Locascio**, North Potomac, MD (US); **Susan L. R. Barker**, Charlottesville, VA (US); **David Ross**, Germantown, MD (US); **Michael J. Tarlov**, Bethesda, MD (US)

(73) Assignee: **The United States of America as represented by the Secretary of Commerce**, Washington, DC (US)

(*) Notice: Subject to any disclaimer, the term of this patent is extended or adjusted under 35 U.S.C. 154(b) by 596 days.

(21) Appl. No.: **09/881,123**

(22) Filed: **Jun. 15, 2001**

(65) **Prior Publication Data**

US 2002/0053514 A1 May 9, 2002

Related U.S. Application Data

(60) Provisional application No. 60/232,951, filed on Sep. 15, 2000.

(51) **Int. Cl.⁷** **G01N 27/447**

(52) **U.S. Cl.** **204/601; 204/600; 436/516**

(58) **Field of Search** 204/600, 601; 436/516

(56) **References Cited**

U.S. PATENT DOCUMENTS

5,208,111 A	5/1993	Decher et al.	
5,770,029 A *	6/1998	Nelson et al.	204/604
5,858,188 A *	1/1999	Soane et al.	204/454
6,020,175 A	2/2000	Onda et al.	
6,402,918 B1	6/2002	Schlenoff et al.	

OTHER PUBLICATIONS

Katayama et al. "Stable Cationic Capillary Coating with Successive Multiple Ionic Polymer Layers for Capillary Electrophoresis", *Anal. Chem.*, 1998, v. 70, pp. 5272-5277.*

Tronin et al. "Ellipsometry and x-ray reflectometry characterization of self-assembly process of polystyrene sulfonate and polyallylamine", *Colloid and Polymer Science* (1994), 272(10), 1317-21 (Abstract).*

Stroock et al. "Patterning Electro-osmotic Flow with Patterned Surface Charge", *Phys. Rev. Lett.*, Apr. 10, 2000, v. 84, No. 15, pp. 3314-3317.*

Caruso et al. "Protein Multilayer Formation on Colloids through a Stepwise Self-Assembly Technique", *J. Am. Chem. Soc.*, 1999, v. 121, pp. 6039-6046.*

Barker et al. "Control of Flow Direction in Microfluidic Devices with Polyelectrolyte Multilayers", *Anal. Chem.*, 2000, v. 72, pp. 5925-5929.*

Ladam et al. "Protein Interactions with Polyelectrolyte Multilayers: . . .", *Biomacromolecules*, 2000, v. 1, pp. 674-687.*

Pfohl et al. "Controlled Modification of Microstructures Silicon Surfaces for Confinement of Biological Macromolecules and Liquid Crystals", *Langmuir*, 2001, v. 17, pp. 5343-5351.*

(List continued on next page.)

Primary Examiner—Yelena G. Gakh

(74) *Attorney, Agent, or Firm*—Stites & Harbison PLLC; Ross F. Hunt, Jr.

(57) **ABSTRACT**

A microchannel device is provided with a plastic substrate having a microchannel formed therein. Polyelectrolyte multilayers are disposed along selected surfaces of the microchannel. The polyelectrolyte layers comprise alternating net positively charged layers and net negatively charged layers. A microchannel lid has a surface facing the microchannel. In making the microchannel device, selected surfaces of the microchannel are alternatively exposed to solutions comprising positively charged polyelectrolytes and negatively charged polyelectrolytes to form the desired number of polyelectrolyte layers.

42 Claims, 4 Drawing Sheets

